Low odor UV varnish

Function introduction :

Is a uv curing varnish, wide applicability and other characteristics, is a high comprehensive performance of a product .

Product specification :

Appearance	Pale yellow transparent liquid
Viscosity (25℃ tu-4 cup)	30-40″
Solid content	96%±2%
Glossiness	≥90°
Wear resistence (4 lb)	≥800 times
Cure condition	Speed above 2m/s ,UV light intensity 80w/cm

Using method :

◎Stir thoroughly before use, leave for 3-5 minutes for printing, seal and store after use

◎UV curing immediately after using ;

◎When the screen plate is closed, it must be cleaned with plate cleaner, and the solvent must be completely volatilized before printing ;

◎When printing a particularly thick ink layer, considering that the heat is too high after printing, use a dry frame or erected tort of the heat volatilization after stacking

◎Adjust the printing scraper tilt, printing machine function to stop, mesh thinning, printing scraper pressure adjustment can increase the thickness of UV varnish. The speed of UV light fixing machine and the ambient temperature can affect the surface leveling

◎Recommended use of solvent - resistant, alkali - resistant and alcohol - resistant ink print ;

◎ Recommended to add 5%-10% thinner for dilution ;

◎If drying is too slow, the paper walking speed can be appropriately reduced. If the drying is still not complete, maybe the power of the UV lamp is too low. recommended that the lamp be replaced after 800 hours by the radiometer

◎This product has a certain irritation, avoid direct skin contact, if contact with detergent to clean ;

◎This product should be placed in a cool, dry and ventilated condition, avoid direct sunlight, away from heat source 。

Packing：

20KG black plastic barrel